



The Kenya Power & Lighting
Co. Ltd.

TITLE:

SPECIFICATION FOR HIGH
CONDUCTIVITY ALUMINIUM ALLOY
TUBES FOR ELECTRICAL PURPOSES
(Substation Busbars)

Doc. No.

KPLC1/3CB/TSP/06/39

Issue No.

1

Revision
No.

0

Date of
Issue

2012-09-28

Page 1 of 8

TABLE OF CONTENTS

0.1 Circulation List

0.2 Amendment Record

FOREWORD

1. SCOPE
2. REFERENCES
3. TERMS AND DEFINITIONS
4. REQUIREMENTS
5. TESTS AND INSPECTION
6. MARKING AND PACKING

ANNEX A: Guaranteed Technical Particulars (to be filled and signed by the Manufacturer and submitted together with relevant copies of the Manufacturer's catalogues, brochures, drawings, technical data, sales records, customer reference letters, details of manufacturing capacity, the manufacturer's experience and copies of test reports for tender evaluation, all in the English Language)

Issued by: Head of Section, Tech Stds & Specs

Signed:

Date: 2012-09-28

Authorized by: Head of Department, R&D

Signed:

Date: 2012-09-28



The Kenya Power & Lighting
Co. Ltd.

TITLE:

**SPECIFICATION FOR HIGH
CONDUCTIVITY ALUMINIUM ALLOY
TUBES FOR ELECTRICAL PURPOSES
(Substation Busbars)**

Doc. No. KPLC1/3CB/TSP/06/39

Issue No. 1

Revision
No. 0

Date of
Issue 2012-09-28

Page 4 of 8

4.1.1 The aluminium alloy tubes shall be suitable for use outdoors in tropical climate with maximum ambient temperature of 40°C, heavy polluting saline conditions and humidity of up to 90%.

4.1.2 The aluminium alloy tubes shall be designed for use as busbars in substations operating at maximum system voltages of 145kV, 50Hz.

4.2 Materials and Construction

4.2.1. The tubes shall be round, seamless, extruded round tubes of high conductivity aluminium alloy for electrical purposes (including substation busbars) manufactured to relevant parts of BS EN 755.

4.2.2. The tubes shall be produced by the seamless die/mandrel method of extrusion.

4.2.3. The tubes shall not be re-drawn/extruded from used tubes.

4.2.4. The tubes shall be supplied in straight lengths (as specified) and the ends shall be cut clean and square with the axis of the tube.

4.2.5. The tubes shall be new, clean, smooth, free from harmful defects and free from any surface defects. They shall be free from sharp edges, abrasions and cuts.

4.2.6. The tubes shall have adequate strength to withstand mechanical forces due to short circuit current of 40kA for 3 seconds.

4.2.7. The temperature of the tubular bus when carrying full load current shall not exceed 50° C above ambient temperature.

4.3 Dimensions

The aluminium alloy tubes shall be in the following sizes and indicated tolerances:

Outside Diameter		Wall thickness		Length	
Size (mm)	Tolerance (mm)	Thickness (mm)	Tolerance (%)	Size (m)	Tolerance (%)
40	±0.35	4.0	±8	6.0	+10, 0
50	±0.35	8.0	±8	6.0	+10, 0
80	±0.35	10.0	±8	6.0	+10, 0

Issued by: Head of Section, Tech Stds & Specs

Signed:

Date: 2012-09-28

Authorized by: Head of Department, R&D

Signed:

Date: 2012-09-28



The Kenya Power & Lighting
Co. Ltd.

TITLE:

SPECIFICATION FOR HIGH
CONDUCTIVITY ALUMINIUM ALLOY
TUBES FOR ELECTRICAL PURPOSES
(Substation Busbars)

Doc. No. KPLC1/3CB/TSP/06/39

Issue No. 1

Revision No. 0

Date of Issue 2012-09-28

Page 5 of 8

4.4 Chemical Composition, Mechanical and Physical Properties

The aluminium alloy tubes shall be of high conductivity material with the following properties:

4.4.1 Chemical Composition (to BS EN 573-3)

Element	Si	Fe	Cu	Mn	Cr	Zn	Ti	others		Al
								each	total	
Limits (weight %)	0.30-0.60	0.10-0.30	max. 0.05	max. 0.05	-	max. 0.10	-	max. 0.03	max. 0.10	remainder

4.4.2 Mechanical Properties (to BS EN 755-2)

Description	Temper	Yield stress Mpa	Tensile strength Mpa	Hardness HB	Elongation	
					A %	A _{50mm} %
Required	T6	160	215	65	8	6

4.4.3 Physical Properties

Description	Required	
Density (at 20°C)	2690 Kg/m ³	
Melting range (at 20°C)	585-650 °C	
Electrical conductivity (at 20°C)	≥30 MS/m	
Thermal conductivity (at 20°C)	218 W/m.K	
Co-efficient of thermal expansion (at 20°C)	23.5 x 10 ⁻⁶ /K	
Modulus of elasticity (at 20°C)	~70 GPa	
Mass per unit length (at 20°C)	40mm o.d., 4mm thickness	1.2 Kg/m
	50mm o.d., 8mm thickness	2.9 Kg/m
	80mm o.d., 10mm thickness	5.9 Kg/m
Second moment (at 20°C)	40mm o.d., 4mm thickness	7 cm
	50mm o.d., 8mm thickness	24 cm
	80mm o.d., 10mm thickness	137 cm
Current carrying capacity (busbar temperature of 80 °C, ambient temperature of 35 °C)	40mm o.d., 4mm thickness	940 A
	50mm o.d., 8mm thickness	1540 A
	80mm o.d., 10mm thickness	2580 A

Issued by: Head of Section, Tech Stds & Specs

Authorized by: Head of Department, R&D

Signed:

Signed:

Date: 2012-09-28

Date: 2012-09-28



The Kenya Power & Lighting
Co. Ltd.

TITLE:

**SPECIFICATION FOR HIGH
CONDUCTIVITY ALUMINIUM ALLOY
TUBES FOR ELECTRICAL PURPOSES
(Substation Busbars)**

Doc. No.

KPLC1/3CB/TSP/06/39

Issue No.

1

Revision
No.

0

Date of
Issue

2012-09-28

Page 6 of 8

5 TESTS AND INSPECTION

5.1 The aluminium alloy tubes shall be tested in accordance with relevant parts of BS EN 755 and the requirements of this specification. It shall be the responsibility of the supplier to perform or to have performed all the relevant tests.

5.2 Copies of previous test reports by a third party testing laboratory accredited to ISO/IEC 17025 shall be submitted with the offer for evaluation (all in English Language). A copy of accreditation certificate (to ISO/IEC 17025) for the testing laboratory shall also be submitted with the tender for evaluation.

Copies of test reports to be submitted for tender evaluation shall include dimensions, chemical composition, mechanical and physical properties tests.

The Manufacturer's Declaration of Conformity to the reference standards shall also be submitted with the tender.

5.3 Routine and sample test reports (including dimensions, chemical composition, mechanical and physical properties) for the aluminium alloy tubes to be supplied shall be submitted to Kenya Power for approval before shipment/delivery of the goods. Kenya Power will witness acceptance tests at the factory before shipment.

5.4 On receipt of the goods Kenya Power may perform any of the relevant tests in order to verify compliance with this specification. The supplier shall replace without charge to Kenya Power aluminium alloy tubes which upon examination, test or use fail to meet any of the requirements in the specification.

6 MARKING AND PACKING

6.1 The aluminium alloy tubes shall be engraved legibly and indelibly with the following information, all in the English language:

- Name of the manufacturer
- Year of manufacture
- Product Designation (including dimensions)
- Standard to which the aluminium alloy tubes comply

6.2 The aluminium alloy tubes shall be supplied in bundles wrapped in plastic foil.

-----THIS SPACE LEFT BLANK-----

Issued by: Head of Section, Tech Stds & Specs

Authorized by: Head of Department, R&D

Signed:

Signed:

Date: 2012-09-28

Date: 2012-09-28



The Kenya Power & Lighting
Co. Ltd.

TITLE:

**SPECIFICATION FOR HIGH
CONDUCTIVITY ALUMINIUM ALLOY
TUBES FOR ELECTRICAL PURPOSES
(Substation Busbars)**

Doc. No.	KPLC1/3CB/TSP/06/39
Issue No.	1
Revision No.	0
Date of Issue	2012-09-28
Page 7 of 8	

ANNEX A: Guaranteed Technical Particulars (to be filled and signed by the Manufacturer and submitted together with relevant copies of the Manufacturer's catalogues, brochures, drawings, technical data, sales records, customer reference letters, details of manufacturing capacity, the manufacturer's experience and copies of test reports for tender evaluation, all in the English Language)

TENDER NO

Clause	Description	Bidder's offer	
-	Name of the Manufacturer, address and Country of manufacturing		
	Name & address of Bidder		
	Type/Model Reference Number of items offered		
1	Scope: It shall be the responsibility of the supplier to ensure adequacy of the design, good workmanship and good engineering practice in the manufacture of the aluminium alloy tubes for Kenya Power		
2	Applicable Standards		
3	Terms and Definitions		
4.1	General Requirements: 4.1.1 & 4.1.2		
4.2	Materials and Construction		
	4.2.1		
	4.2.2		
	4.2.3		
	4.2.4		
	4.2.5		
	4.2.6		
	4.2.7		
4.3	Dimensions	Outside diameter (mm)	
		Wall thickness (mm)	
		Length (m)	
4.4.1	Chemical Composition to BS EN 573-3	Silicon, Si (%)	
		Iron, Fe (%)	
		Copper, Cu (%)	
		Manganese, Mn (%)	
		Chromium, Cr (%)	
		Zinc, Zn (%)	
		Titanium, Ti (%)	
		Others	each
			total
4.4.2	Mechanical Properties	Temper	

Issued by: Head of Section, Tech Stds & Specs

Authorized by: Head of Department, R&D

Signed:

[Signature]

Signed:

[Signature]

Date: 2012-09-28

Date: 2012-09-28



The Kenya Power & Lighting
Co. Ltd.

TITLE:

**SPECIFICATION FOR HIGH
CONDUCTIVITY ALUMINIUM ALLOY
TUBES FOR ELECTRICAL PURPOSES
(Substation Busbars)**

Doc. No.

KPLC1/3CB/TSP/06/39

Issue No.

1

Revision
No.

0

Date of
Issue

2012-09-28

Page 8 of 8

	(to BS EN 755-2)	Yield stress (MPa)	
		Tensile strength (MPa)	
		Hardness (HB)	
		Elongation (%)	A
			A _{50mm}
4.4.3	Physical Properties, 20 °C	Density (Kg/m ³)	
		Melting range (°C)	
		Electrical conductivity (MS/m)	
		Thermal conductivity (W/m.K)	
		Co-efficient of thermal expansion (10 ⁻⁶ /K)	
		Modulus of elasticity (GPa)	
	Mass per unit length, Kg/m (at 20°C)	40mm o.d., 4mm thickness	
		50mm o.d., 8mm thickness	
		80mm o.d., 10mm thickness	
	Second moment, cm (at 20°C)	40mm o.d., 4mm thickness	
		50mm o.d., 8mm thickness	
		80mm o.d., 10mm thickness	
	Current carrying capacity, A (busbar temperature of 80 °C, ambient of 35 °C)	40mm o.d., 4mm thickness	
		50mm o.d., 8mm thickness	
		80mm o.d., 10mm thickness	
5	Tests and Inspection: 5.1		
	5.2		
	5.3		
	5.4		
6	Marking and Packing: 6.1		
	6.2		
-	List of copies of Test Reports submitted		
-	Manufacturer's Declaration of Conformity		
-	List of Acceptance Tests to be witnessed by Kenya Power at the factory before shipment		
-	Catalogues, brochures, technical data, and drawings		
-	Customer sales records and customer reference letters submitted to support the offer.		

.....
Manufacturer's Name, Signature, Stamp and Date

Issued by: Head of Section, Tech Stds & Specs

Authorized by: Head of Department, R&D

Signed:

Signed:

Date: 2012-09-28

Date: 2012-09-28